

Shredded Clay : คุณสมบัติทางเคมี

Type	SPECIFICATION			
	%Al ₂ O ₃	%Residue #120	%LOI	%Fe ₂ O ₃
S	26.0 - 23.5	2.5 - 0.0	11.0 - 9.0	3.5 -1.5
IT A	28.0 - 25.0	2.6 - 0.4	14.0 -7.5	3.0 - 1.2
IT B	26.0 - 23.0	4.0 - 2.0	14.0 -7.5	3.0 - 1.2
G A	24.0 - 22.0	3.0 - 0.5	10.5 - 8.0	3.0 - 0.0
G B	24.0 - 22.0	3.0 - 0.5	10.5 - 8.0	3.0 - 6.0
T A	23.0 - 17.0	4.0 - 0.0	10.5 - 6.0	1.5 - 0.0
T B	23.0 - 17.0	4.0 - 0.0	10.5 - 6.0	3.0 - 1.5
Sc A	28.5 - 23.0	6.0 - 2.5	16.5 - 9.5	3.0 - 0.0
Sc B	28.5 - 23.0	11.0 - 4.5	20.5 - 13.0	6.0 - 1.5
IB A	27.0 - 19.0	9.5 - 3.5	16.0 - 4.5	1.5 - 0.0
IB B	27.0 - 19.0	14.5 - 9.5	16.0 - 4.5	1.5 - 0.0
IB C	27.0 - 19.0	12.5 - 3.5	16.0 - 8.5	3.0 - 1.5
IB D	27.0 - 19.0	14.5 - 6.5	16.0 - 4.5	3.0 - 1.5
IB E	27.0 - 19.0	14.5 - 4.5	16.0 - 4.5	6.0 - 3.0
Outlier	Various properties			